

Magnetic Tunnel Window's Imprint and Beyond

Juan J. Alonso^a, Julio F. Fernández^b

^a*Departamento Física Aplicada, Universidad de Málaga, Málaga, 29071 (Spain)*

^b*ICMA, CSIC and Universidad de Zaragoza, 50009-Zaragoza (Spain)*

Abstract

We report results from Monte Carlo simulations of systems of magnetic dipoles that relax through quantum tunneling, much as Fe₈ crystals at very low temperature. For short times, a hole develops in suitably defined magnetic field pseudo-distributions, which matches the shape of the tunnel window (TW). Much later, ordinary field distributions $P(h)$ develop similar holes if thermal energies are not much larger than the TW's energy. Still later, below the long-range ordering (LRO) temperature, $P(h)$ exhibits the signature of LRO.

Key words: quantum tunneling, magnetization processes, dipolar interactions, cooling history, dipole field distributions
PACS: 75.45.+j, 75.50.X.x

Magnetic relaxation in crystals of single-molecule magnets, such as Fe₈, has recently become a subject of great interest. Experimentally observed relaxation at temperatures T that are below some 10^{-2} of single-ion crystal anisotropy barrier energies U is temperature independent, and is duly attributed to magnetic quantum tunneling (MQT) [1]. As explained in Ref. [2], hyperfine interactions with nuclear spins open up tunneling windows (TW's) of energy ε_w that are comparable to magnetic dipolar energies. Then,

$$\Gamma'(\varepsilon_h) \simeq \Gamma \eta(\varepsilon_h/\varepsilon_w), \quad (1)$$

is the tunneling rate for spins at very low temperature, where Γ is some rate, $\eta(x) \sim 1$ for $|x| \lesssim 1$, $\eta(x) \sim 0$ for $|x| \gtrsim 1$, and $2\varepsilon_h$ is the Zeeman energy change upon tunneling. From here on, times are given in terms of Γ^{-1} . The results reported here in Figs. 1, 2(a), and 3 are for $\eta(x) = 1$ for $|x| < 1$ and $\eta(x) = 0$ for $|x| > 1$; in Fig. 2(b) we show results for $\eta(x) = \exp(-|x|)$. We shall refer to the former TW as *flat* and to the latter one as *exponential*. An unusual magnetiza-




Fig. 1. f/h versus h for the shown times after quenching and applying a field $H = 2$. All data points are for averages over 4×10^5 independent runs for $\varepsilon_w = 0.1$. In the inset, $\bullet$ and $\circ$ are for P_+ and P_- .

tion M relaxation of fully polarized Fe₈ like systems, $M_{t=0} - M_t \propto \sqrt{t}$, was predicted in Ref. [2] and later observed [3]. In an important piece of work, Wernsdorfer et al. [4] found that $M_t \propto \sqrt{t}$ if a small magnetic field H is applied at $t = 0$, after quenching from a higher temperature. This behavior has been explained recently [5]. In addition, since $dM_t(H)/dt = -2\Gamma \int dh f(h,t) \eta(h+H)$ at all times, where $f(h,t) = [P_+(h,t) - P_-(h,t)]$, and $P_+(h)$ [$P_-(h)$] is the density distribution for fields

Email addresses: jjalonso@uma.es (Juan J. Alonso),
jff@pipe.unizar.es (Julio F. Fernández).

h acting on up [down] spins, $f(h, t)$ can be determined by a suitable application of magnetic fields. [f itself is not normalized, and is therefore not a distribution. In fact, it turns out that $f(h)$ is proportional to the system's energy [5]]. A “hole” of “intrinsic width”, was thus observed to develop in time, and conjectured to correspond to the width in $\eta(h)$, i.e., to the width of the TW [4].

We report Monte Carlo simulations of Ising systems of interacting dipoles on SC lattices. Initially, spins are allowed to flip readily at temperature $T_a \gtrsim U/10 \gtrsim T_o$ ($T_o \simeq 2.5$ is the LRO temperature) until the energy per spin reaches some value ε_a . A field H is applied then and spins only flip at rate Γ' [see Eq. (1)] thereafter, thus simulating temperatures below some $10^{-2}U$. We have previously found [5] that $M_t \propto |\varepsilon_a| t$. Here, we report results for the evolution of the field pseudo-distribution function $f(h)$ and for $p(H) \equiv P_+(h) + P_-(h)$. Fields and energies are given in terms of nearest neighbor dipolar values.

How $P_+(h)$ and $P_-(h)$ split, leading to a non-vanishing $f(h)$, after thermalization at high T is illustrated in the inset of Fig. 1. The hole that develops in $f(h)$ after quenching and applying field H is shown in Fig. 1. The shape of the hole is shown in Figs. 2(a) and (b), for flat and exponential TW's, respectively, for $H = 2$. Clearly, not only is the hole's width the same as the width of η , as conjectured in Ref. [4], but $f(h)/h$ matches $\eta(h)$ for the three shortest times shown in Figs. 2(a) and (b). When $t \gtrsim 1$, the hole widens, as shown in Fig. 2(a) for $t = 4$.

On the time scale on which the hole in f/h develops, $P(H)$ remains approximately independent of time. On the other hand, a hole which resembles the TW grows at much later times in $P(H)$ if $T \lesssim \varepsilon_w$ [6]. This is exhibited in Fig. 3. Still later, below the long-range ordering (LRO) temperature, $P(h)$ exhibits the signature of LRO [7] whether $T \lesssim \varepsilon_w$ or not. If, on the other hand, the energy of the system is kept constant, no LRO ensues, as expected. This is illustrated in Fig. 3.

References

- [1] C. Sangregorio *et al.*, Phys. Rev. Lett. **78**, 4645 (1997).
- [2] N. V. Prokof'ev and P. C. E. Stamp, Phys. Rev. Lett. **80**, 5794 (1998).
- [3] T. Ohm, C. Sangregorio, and C. Paulsen, Eur. Phys. J. B **6**, 195 (1998).
- [4] W. Wernsdorfer *et al.*, Phys. Rev. Lett. **82**, 3903 (1999).




Fig. 2. (a) f/h versus h for short times with a flat TW of $\varepsilon_w = 0.1$, $H = 2$ and $\varepsilon_a = -0.51$ (b) Same as in (a) but for an exponential, TW with $\varepsilon_w = 0.1$. The solid line, $\circ$, $\square$, $\diamond$ and $\triangle$ are for $t = 0, 0.0625, 0.25, 0.5$ and 4 , respectively.

- [5] J. F. Fernández and J. J. Alonso, Phys. Rev. Lett. (in press).
- [6] J. J. Alonso and J. F. Fernández, Phys. Rev. Lett. **87**, 097205 (2001).
- [7] J. F. Fernández, Phys. Rev. B **66**, 064423 (2002).




Fig. 3. The field distribution P versus h for the shown times, and $T = 0.1$ or constant energy. In all cases $\varepsilon_a = -0.58$, $\varepsilon_w = 0.2$ and $H = 1$.